

ABSTRACT

The invention is directed to an adsorbent comprising: a) 20-30 % porous carbon with incorporated organic nitrogen species; and b) 70-80% inorganic matter. The invention is directed to a method of making an adsorbent which comprises: a) thermally drying dewatered sewage sludge to form granulated organic fertilizer; and b) pyrolyzing said the organic fertilizer at temperatures between 600 and 1000 °C. The invention is additionally directed to the process of removing acidic gases from wet air streams comprising putting an adsorbent in contact with the wet air stream and allowing the adsorbent to adsorb the acidic gases.

09597398 112901
10521 9526550